



HALF-CELL BIFACIAL MODULE

TYPE: STPXXXS-C72/Pmh+

545-565W 21.9%

POWER OUTPUT

MAX EFFICIENCY

IEC 61701 Salt-mist Certification

IEC 62716 Ammonia Certification

IEC 60068-2-68 Dust and Sand

IEC 61730-2 (UL790) Fire Class C



Compatible with mainstream trackers

The module design is highly compatible with power plant tracking systems, which offers a cost-effective solution for large power plants



Anti-PID guarantee

Through the optimization of cell technology and material, the decay caused by PID phenomenon is reduced



Double-sided power generation

The gain of double-sided power generation increases up to max. 25% with the light on the back side, and significantly reduce LCOE



Extended wind and snow load tests

Module certified to withstand extreme wind (2400 Pascal) and snow loads (5400 Pascal)*
















30 years of linear warranty

15 years of product warranty

ISO 14001 **Environment Management System** ISO 45001 Occupational Health and Safety ISO 9001 Quality Management System SA 8000 Social Responsibility Standards IEC TS 62941Guideline for Module Design

Munich RE



First year power degradation 2% Annual degradation 0.45%

^{*} Please refer to Suntech Standard Module Installation Manual for details.

^{***} WEEE only for EU market.

^{**} Please refer to Suntech Limited Warranty for details.


^{****} Suntech reserves the right to the final.





Mechanical Characteristics

Solar Cell	P-type monocrystalline silicon
No. of Cells	144 (6 × 24)
Dimensions	2278 × 1134 × 30 mm (89.7 × 44.6 × 1.2 inches)
Weight	32.0 kg (70.5 lbs.)
Front \ Back Glass	2.0+2.0 mm (0.079+ 0.079inches) semi-tempered glass
Output Cables	4.0 mm², (-) 350 mm and (+) 160 mm in length or customized length
Junction Box	IP68 rated (3 bypass diodes)
Operating Module Temperature	-40 °C to +85 °C
Maximum System Voltage	1500 V DC (IEC)
Connectors	STP-XC4
Maximum Series Fuse Rating	25 A
Power Tolerance	0/+5 W
Refer. Bifaciality Factor	(70 ± 5)%
Frame	Anodized aluminum alloy frame
Packing Configuration	36 pieces per pallet 720 pieces per container /40'HC 2310×1120×1255mm per pallet 1202kg per pallet



For tracker installation, please turn to Suntech for mechanical load information.

Electrical Characteristics

Module Type	STP565S-	C72/Pmh+	STP560S-	-C72/Pmh+	STP555S-	C72/Pmh+	STP550S-	C72/Pmh+	STP545S-	C72/Pmh+
Testing Condition	STC	NMOT	STC	NMOT	STC	NMOT	STC	NMOT	STC	NMOT
Maximum Power (Pmax/W)	565	429	560	425	555	421	550	418	545	414
Optimum Operating Voltage (Vmp/V)	42.58	39.40	42.40	39.20	42.24	39.00	42.05	38.90	41.87	38.70
Optimum Operating Current (Imp/A)	13.27	10.90	13.21	10.85	13.14	10.80	13.08	10.75	13.02	10.71
Open Circuit Voltage (Voc/V)	50.41	47.50	50.23	47.40	50.07	47.20	49.88	47.00	49.69	46.90
Short Circuit Current (Isc/A)	14.20	11.46	14.14	11.41	14.07	11.35	14.01	11.30	13.96	11.26
Module Efficiency (%)	21	1.9	2	1.7	21.5		21.3		2	1.1

STC: Irradiance 1000 W/m², module temperature 25 °C, AM=1.5; NMOT: Irradiance 800 W/m², ambient temperature 20 °C, AM=1.5, wind speed 1 m/s; Measuring tolerance is within +/- 3%;


Different Rearside Power Gain Reference to 555W Front

Rearside Power Gain	5%	15%	25%
Maximum Power at STC (Pmax)	583	638	694
Optimum Operating Voltage (Vmp/V)	42.24	42.24	42.34
Optimum Operating Current (Imp/A)	13.80	15.11	16.43
Open Circuit Voltage (Voc/V)	50.07	50.07	50.17
Short Circuit Current (Isc/A)	14.77	16.18	17.59
Module Efficiency (%)	22.6	24.7	26.9

Temperature Characteristics

Nominal Module Operating Temperature (NMOT)	42 ± 2 °C
Temperature Coefficient of Pmax	-0.34%/°C
Temperature Coefficient of Voc	-0.26%/°C
Temperature Coefficient of Isc	0.050%/°C

Graphs Current-Voltage & Power-Voltage (555W)



Information on how to install and operate this product is available in the installation instruction. All values indicated in this data sheet are subject to change without prior announcement. The specifications may vary slightly. All specifications are in accordance with standard EN 50380. Color differences of the modules relative to the figures as well as discolorations of/in the modules which do not impair their proper functioning are possible and do not constitute a deviation from the specification.